

ECCOSORB® CRS

High-Loss, Two-Part Castable RTV Silicone Absorber

Material Characteristics

- Castable RTV silicone rubber with high-loss in the microwave frequency range. Dark gray in color.
- When fully cured, ECCOSORB® CRS will duplicate the electrical properties of its counterpart in the ECCOSORB® MFS series. For example, ECCOSORB® CRS-117 is electrically equivalent to ECCOSORB® MFS-117.
- Being a true elastomer, ECCOSORB® CRS when cured, has a number of distinct advantages over rigid materials of the ECCOSORB® MF type.
- For electrical and physical properties of the ECCOSORB® CRS series, please see the Technical Bulletin on ECCOSORB® MF.
- Frequency range from 1 - 18 GHz
- Low out-gassing properties

Applications

- ECCOSORB® CRS can be used to cast cones, wedges, and pyramids for terminations and loads
- It can also be used to fill cavities or be painted on surfaces to suppress the flow of currents. Therefore, ECCOSORB® CRS finds use in antennas and transmission lines. It has also been poured around the base of microwave tubes to prevent undesired energy flow
- ECCOSORB® CRS can also be poured in place to form microwave gaskets
- When bonded to surfaces, ECCOSORB® CRS will withstand temperature cycling (even to cryogenic temperatures). It can be deformed and shaped to contoured surfaces and is not subject to damage from impact or shock

Availability

- ECCOSORB® CRS is supplied as a two component system consisting of a Component A and Component B in 2 pound (quart) and 8 pound (gallon) kits. It does not ship as a dangerous good.
- Both CRS-117 and CRS-124 are available in premixed and frozen 5cc, 10cc, and 30cc syringes. No Mixing is needed. Note: Premixed and frozen packaging requires storage at -40°F (-40°C) and shelf life is 3 months. Minimum buy is 100 syringes for any size.
- Shelf life is approximately 6 months when stored unmixed in a well sealed container. This material can be stored frozen to increase shelf life.

Instructions for Use

- Part A is supplied as a high viscosity paste. In all cases a small amount of Part B is added. *See table below for actual mix ratios by weight*
- To insure void-free castings, the entrapped air should be removed by vacuum de-airing
- The mixture converts to flexible, high temperature silicone rubber at room over night or elevated temperatures of 175 °F for 3 hours. Where use temperature is anticipated above 250 °F (121°C), a post cure is recommended. Gradually raise cast parts to the use temperature over an 8 hour or longer period
- If cast around inserts, they place negligible curing pressures on them
- The ECCOSORB® CRS will adhere to themselves but will release from most other surfaces. Therefore, metal or epoxy molds are suitable for cast shapes. If adhesion is required, a primer must first be used
- Members of the ECCOSORB® CRS series can be bonded to other materials with ECCOBOND® TP-50. A wipe-on coat of ECCOBOND® TP-50 will give cast or molded pieces extra environmental protection

Typical Properties

	CRS-117	CRS-124
Density, g/cc	4.16	4.55
Max. Service Temperature, °F (°C)	320 (160)	320 (160)
Thermal Expansion, °F (°C)	35 x 10 ⁻⁶ (63 x 10 ⁻⁶)	33 x 10 ⁻⁶ (59 x 10 ⁻⁶)
Thermal Conductivity, (cal)(cm)/(sec)(cm ²)(°C) (BTU)(in)/(hr)(ft ²)(°F)	0.0021 6.0	0.0024 7.0
Hardness, Shore A	75	75
Water Absorption, % 24 hours	<0.1	<0.1
Dielectric Strength, volts/mil (Kv/cm)	>10 (>4)	>10 (>4)
Volume Resistivity, ohm-cm	>10 ¹⁰	>10 ¹⁰
Relative Impedance, Z/Zo	0.3	0.4
Mix Ratio by weight, A:B	100:1.18	100:1



Typical Attenuation

	GHz	10 ⁻⁷	10 ⁻⁶	10 ⁻⁵	10 ⁻⁴	10 ⁻³	10 ⁻²	10 ⁻¹	1.0	3.0	8.6	10.0	18.0
CRS-117	dB/cm	0	0	0	0	0	0.03	0.27	2.8	11	46	56	119
	dB/in	0	0	0	0	0	0.08	0.69	7.1	28	117	142	302
CRS-124	dB/cm	0	0	0	0	0	0.03	0.48	6.5	20	63	67	149
	dB/in	0	0	0	0	0	0.08	1.2	1.7	50	160	170	378

*Note: Attenuation is a theoretical property calculated from the Complex Permittivity and Complex Permeability of a lossy material and is strictly a means of comparing one absorbing material to another. The attenuation properties are not an indication of how the material will perform inside a microwave device. For further electrical and physical properties of the ECCOSORB® CRS series, please see the Typical Electrical Properties Table on the ECCOSORB® MFS technical bulletin

EMERSON & CUMING MICROWAVE PRODUCTS, INC., 28 York Avenue, Randolph, MA 02368 / Telephone (781) 961-9600. Use of Information and Material: Values shown are based on testing of laboratory test specimens and represent data that falls within normal range of the material. These values are not intended for use in establishing maximum, minimum or ranges of values for specification purposes. Any determination of the suitability of the material for any purpose contemplated by the user and the manner of such use is the responsibility of the user. The user should determine that the material meets the needs of the user's product and use. We hope that the information given here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for the user's consideration, investigation and verification but we do not warrant the results to be obtained. Please read all statements, recommendations or suggestions in conjunction with our conditions of sale INCLUDING THOSE LIMITING WARRANTIES AND REMEDIES, which apply to all goods supplied by us. We assume no responsibility for the use of these statements, recommendations or suggestions nor do we intend them as a recommendation for any use, which would infringe any patent or copyright. Emerson & Cuming Microwave Products Inc.